



(19)

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 330 180 B2

(12)

NEW EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the opposition decision:
03.03.1999 Bulletin 1999/09

(51) Int. Cl.⁶: **A61K 9/16, A61K 9/52**

(45) Mention of the grant of the patent:
13.01.1993 Bulletin 1993/02

(21) Application number: 89103091.8

(22) Date of filing: 22.02.1989

(54) **Polylactic acid type microspheres containing physiologically active substance and process for preparing the same**

Physiologisch aktive Substanzen enthaltende Mikrosphären des Polymilchsäuretyps sowie Verfahren zu deren Herstellung

Microsphères du type acide polylactique contenant des substances physiologiquement actives et leur procédé de préparation

(84) Designated Contracting States:
CH DE FR GB IT LI NL

(30) Priority: 24.02.1988 JP 42459/88

(43) Date of publication of application:
30.08.1989 Bulletin 1989/35

(73) Proprietor:
Biomaterials Universe, Inc.
Kyoto-shi Kyoto-fu (JP)

(72) Inventors:
• Hyon, Suong-Hyu
Uji-shi Kyoto-fu (JP)
• Ikada, Yoshito
Uji-shi Kyoto-fu (JP)

(74) Representative:
Kraus, Walter, Dr. et al
Patentanwälte Kraus, Weisert & Partner
Thomas-Wimmer-Ring 15
80539 München (DE)

(56) References cited:

EP-A- 25 698	EP-A- 52 510
EP-A- 92 918	EP-A- 134 318
EP-A- 145 240	EP-A- 166 596
EP-A- 172 422	EP-A- 251 476
EP-A- 256 726	EP-A- 274 961
EP-A- 0 058 481	EP-A- 0 134 318
EP-A- 0 145 240	EP-A- 0 274 961
US-A- 3 773 919	US-A- 4 389 330

- J.R. Lawter Proceed. Intern. Symp. Contrl. Rel. Bioact. Mater. 14 (1987), p. 99-100
- L.M. Sanders et al., J. Controlled Release 2 (1985), 187-195
- "Extended Release Dosage Forms", Krowczynski, 1987, p. 70-73
- "Controlled release Systems" D. Hsieh (1988) 84-85

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

EP 0 330 180 B2

Description

[0001] The present invention relates to release-controlled polylactic acid type microspheres containing a water soluble physiologically active substance and a process for preparing the same.

5 [0002] There is a much increasing interest in developing a new drug delivery system (DDS) in recent years. This is due to a social requirement for attaining both safety and high biological availability of drug, i.e. to maximize a pharmaceutical activity of known drug as well as to minimize a side effect thereof. In the DDS study, a commonly employed pharmaceutical carrier is a nondegradable high molecular weight compound such as silicone rubber, polyethylene or ethylene-vinyl acetate copolymer. These carriers have given a good result in a percutaneous preparation which is administered through skin or mucosa. However, when these high molecular weight compounds are implanted or injected into human body, these carriers remain in the body as a foreign material after release of the drug, which causes a certain trouble for the body. On the contrary, if a high molecular weight compound degradable and absorbable *in vivo* is employed as the carrier, the carrier is gradually hydrolyzed in the living tissue and simultaneously the drug contained therein is gradually released, and hence, there is not required any surgical treatment to take out the carrier after the treatment.

15 [0003] The high molecular weight compound degradable and absorbable *in vivo* includes a natural high molecular weight compound, typical example of which is collagen, and a synthetic high molecular weight compound, typical example of which is polylactic acid. The polylactic acid is synthesized from lactic acid which is widely distributed in nature. Besides, this polylactic acid is nonenzymatically hydrolyzed *in vivo* and finally exhausted as carbon dioxide and water, and hence, it is an interesting high molecular weight compound degradable and absorbable *in vivo*. It has been, therefore, studied as a release-controlling carrier for various drugs since the 1970s [Suong-Hyu Hyon, Seiyaku Kojo (Pharmaceutical Factory), Vol. 13, No. 10, p552, 1983].

25 [0004] Among the known studies, a representative one is a process which comprises dissolving a hydrophobic drug such as a hormone drug (e.g. estradiol, and the like) in an organic solvent such as benzene together with the polylactic acid and then removing the solvent by distillation to formulate into a film, powder, pellet and the like (Japanese Patent Second Publication No. 17525/1975). There is also known a so-called solvent evaporation drying method which comprises dissolving the polylactic acid and the hydrophobic drug in an organic solvent for dissolving both components, adding a phase-separating agent to the solution to cause emulsification and then removing the solvent by distillation to collect microparticles (Japanese Patent First Publication No. 33414/1980). However, these methods are applicable only to hydrophobic drug since they employ an hydrophobic organic solvent such as benzene, chloroform, or the like.

30 [0005] On the other hand, for a release-controlled preparation of a water soluble drug by the polylactic acid type high molecular weight compound, there have been attempted the following procedures. Japanese Patent First Publication No. 100516/1985 discloses a procedure wherein a three-layer emulsion of W/O/W type is formed and subjected to drying in water to give microcapsules of polylactic acid. However, this procedure has various disadvantages, i.e. a troublesome process for preparation, a requirement of the third component such as gelatin in addition to the drug and the polylactic acid, difficulty to obtain microspheres in submicron order and a low rate of incorporation of the drug into capsules due to three-layer structure, and occurrence of burst induced by a damage of the polylactic acid wall of the microsphere due to a thin wall of the microcapsules, which results in an unstable release of the drug.

40 [0006] Japanese Patent First Publication No. 150609/1982 describes in detail a sustained release of a polypeptide stable to an acid wherein hydrophobic polylactic acid and a hydrophilic polypeptide are dissolved in a mixture of dioxane and water. However, since at least one of the polylactic acid and the polypeptide is not completely dissolved in the mixture, the obtained solution is not clear. Further, in order to avoid undesirable ununiformity of the polylactic acid and the polypeptide, a film prepared by a casting method is further subjected to a compression molding with a hot press to formulate into a polypeptide-containing polylactic acid film, sheet, cylinder, or pulverized product thereof. Although glacial acetic acid is employed as a solvent of the polylactic acid, a mixed solution of the polylactic acid and the polypeptide is lyophilized and then subjected to an extrusion molding at a high temperature to formulate in a cylinder shape. Thus, this literature does not teach a formulation of the microsphere having a particle size of from 0.01 μ m to 300 μ m like in the present invention.

50 [0007] As is clear from the above description, these known inventions provide with DDS systems having some effects, but are disadvantageous in that they cannot prepare microspheres wherein the hydrophilic physiologically active substance and hydrophobic polylactic acid are uniformly mingled in a molecular order, or in that they include a troublesome procedure for preparation.

55 [0008] EP-A-0 145 240 discloses a microcapsule produced by preparing a water-in-oil emulsion comprising an inner aqueous layer containing said water-soluble drug and a drug retaining substance therefor and an oil layer containing a polymer substance, then thickening or solidifying said inner aqueous layer to a viscosity of not lower than about 5,000 centipoises and finally subjecting the resulting emulsion to in water drying gives prolonged release of said water-soluble drug.

[0009] EP-A-0 134 318 describes long-lasting injectable and implantable insulin compositions provided in the form of

an insulin-biodegradable polymer matrix. The biodegradable polymer is preferably a lactic acid polymer and may be provided in the form of microbeads or pellets.

[0010] Under such circumstances, the present inventors have intensively studied to develop an improved process for preparing of a release-controlled polylactic acid type preparation which is simple and can afford a stable release of an active substance, and have found that there can be obtained microspheric preparation which can attain a sustained release of an active substance for a long period of time with avoiding undesirable occurrence of burst by preparing a solution of a water soluble physiologically active substance and polylactic acid uniformly dissolved in a mixed solvent comprising a hydrophilic organic solvent and water or in an organic acid, mixing the solution with a poor solvent which is immiscible with said mixed solvent or organic acid to give an emulsion, and then subjecting the mixture to the solvent evaporation drying.

[0011] An object of the present invention is to provide a microsphere which comprises polylactic acid selected from the group consisting of an L-lactic acid polymer, a D,L-lactic acid polymer, a copolymer of L-lactic acid and glycolic acid and a copolymer of D,L-lactic acid and glycolic acid, and a water soluble physiologically active substance, selected from the group consisting of a polypeptide type or proteinaceous substance, an antimicrobial agent, an antitumor agent, an antipyretic, an antiinflammatory agent, an analgesic, an antitussive, an expectorant, an antidepressant, a muscle relaxant, an antiulcer agent, an antiallergic agent, a hypotensive, a diuretic, an antidiabetic, a cardiotonic, a vasodilating agent, an antiarrhythmic agent, an anticoagulating agent, a hemostatic agent, a narcotic antagonist, an antitubercular agent, a hormone, an immunoactivator, an antiepileptic agent, an antihistaminic and an agricultural agent, wherein the water-soluble physiologically active substance is uniformly incorporated into the polylactic acid and has a mean particle size of from about 0.01 μm to 300 μm having not more than 30 % of an eluted amount of said physiologically active substance based on the content of said physiologically active substance in the microsphere after 24 hours in *in vitro* elution test in phosphate buffer of pH 7.4 at 37°C, obtainable by a process, which comprises preparing a solution of the water soluble physiologically active substance and the polylactic acid uniformly dissolved in a mixed solvent comprising a hydrophilic organic solvent and water or in an organic acid, mixing the solution with a poor solvent immiscible with said mixed solvent or organic acid to give an O/O type or W/O type emulsion, and subjecting the emulsion to solvent evaporation drying.

[0012] Another object of the present invention is to provide a process for preparing polylactic acid type microspheres containing a water soluble physiologically active substance, which comprises preparing a solution of the water soluble physiologically active substance and the polylactic acid uniformly dissolved in a mixed solvent comprising a hydrophilic organic solvent and water or in an organic acid, mixing the solution with a poor solvent which is immiscible with said mixed solvent or organic acid to give an O/O type or W/O type emulsion, and then subjecting the mixture to the solvent evaporation drying.

[0013] The "water soluble physiologically active substance" in the present invention is a drug showing a high hydrophilicity and a low partition rate in oil and water, but includes those compatible with both oil and water and is selected from the group of hydrophilic anticancer drugs, antibiotics, polypeptides having a physiological activity, antipyretics, sedatives, immunoactivators, antiinflammatory agents, antitussives, antiepileptics, antihistaminics, hypotensives, diuretics, antidiabetics, muscle relaxants, antiulcer agents, antidepressants, antiallergic agents, cardiotonics, antiarrhythmic agents, vasodilating agents, anticoagulating agents, narcotic antagonists, hemostatic agents, antitubercular agents and hormones.

[0014] Preferable examples of the anticancer agents are adriamycin, mitomycin, bleomycin, cisplatin, 5-fluorouracil, methotrexate, actinomycin D, crestin, picibanil and lentinan. The polypeptides having a physiological activity include, for example, insulin, somatostatin, luteinizing hormone releasing hormone (LHRH) and a derivative of LHRH, prolactin, adrenocorticotrophic hormone (ACTH), growth hormone (GH), thyroid-stimulating hormone releasing hormone, melanocyte-stimulating hormone (MSH), luteinizing hormone (LH), palipresin, calcitonin, oxytocin, accessory thyroid hormone, gastrin, tetragastrin hydrochloride, glucagon, pancreozymin, cholecystokinin, angiotensin, human placental lactogen, human chorionic gonadotropin (HCG), enkephalin, endorphin, keutorphin, interferon, interleukin (I, II, III), tumor necrotizing factor (TNF), tuftsin, thymopoietin, thymosin, thymostimulin, thymic humoral factor, blood thymic factor, colony stimulating factor, motiline, deionorphin, bombesin, neurotensin, cerulein, bradykinin, urokinase, asparaginase, kallikrein, substance P, nerve growth factor, blood coagulating factor, lysozyme chloride, polymyxin B, colistin, glamicidin and bacitracin.

[0015] The antibiotics include, for example, tetracyclines (TCs) such as chlortetracycline (CTC), oxytetracycline (OTC), doxycycline (DOXY) and tetracycline (TC); a variety of penicillins (PCs); cephalosporins (CEPs); streptomycin, novabiosin, neomycin, erythromycin, colistin, lincomycin, nalidixic acid, aburamycin, salinomycin, nigericin, kanamycin, kitosomycin, tylosin, furaltadone, vancomycin, thiostrepton, gentamycin, tobramycin, spiramycin, ristocetin, seumycin, erythromycin, 5-O-mycaminoturyronorid and dibekacin hydrochloride.

[0016] The antipyretic, analgesic, antiinflammatory agents include, for example, sodium salicylate, sulpyrin, diclofenac sodium, indomethacin sodium, sodium flufenamate, pethidine hydrochloride, morphine hydrochloride, oxymorphone and levorphanol tartrate.

[0017] The sedatives include, for example, prochlorperazine, trichlorperazine, chlorpromazine hydrochloride, atropine sulfate and scopolamine methylbromide.

[0018] The antitussive expectants include, for example, noscapine hydrochloride, codeine phosphate, methylephedrine hydrochloride, ephedrine hydrochloride, alcloclamide hydrochloride, dihydrocodeine phosphate, chlorphedianol hydrochloride, picoperidamine hydrochloride, cloperastine, isoproterenol hydrochloride, protokytol hydrochloride, salbutamol sulfate and terbutaline sulfate.

[0019] The antidepressants include, for example, phenelzine sulfate, clomipramine, noxiptilin and imipramine.

[0020] The antiepileptics include, for example, ethosuximide, acetazolamide sodium and chlordiazepoxide hydrochloride.

[0021] The muscle relaxants include, for example, pridinol methanesulfonate, pancuronium bromide and tubocurarine chloride.

[0022] The antiulcer agents include, for example, histidine hydrochloride and metoclopramide.

[0023] The antiallergic agents include, for example, ketotifen fumarate, diphenhydramine hydrochloride, chlorpheniramine maleate, methdilazine hydrochloride, tripeleminamine hydrochloride, clemizole hydrochloride, diphenylpyraline hydrochloride and methoxyphenamine hydrochloride.

[0024] The hypotensive, diuretic agents include, for example, clonidine hydrochloride, captopril, bunitrolol hydrochloride, hexamethonium bromide, pentolinium, ecarazine hydrochloride and mecamlamine hydrochloride.

[0025] The antidiabetics include, for example, glipizide, glymidine sodium, phenformin hydrochloride, methformin, and buformin hydrochloride.

[0026] The cardiotonics include, for example, etilefrine hydrochloride, aminophylline, trans- π -oxocamphor and theophyllol.

[0027] The vasodilating agents include, for example, oxyfedrine hydrochloride, tolazoline hydrochloride, diltiazem hydrochloride, bamethan sulfate and hexobendine.

[0028] The antiarrhythmic agents include, for example, propranolol hydrochloride, oxyprenolol hydrochloride, bufetolol hydrochloride and alprenolol hydrochloride.

[0029] The anticoagulating agents include, for example, heparin sodium and sodium citrate.

[0030] The hemostatic agents include, for example, acetomenaphthone, thrombin, thromboplastin, menadione sodium bisulfate, tranexamic acid, ϵ -aminocaproic acid, adrenochrome monoaminoguanidine methansulfonate and carbazochrome sodium sulfate.

[0031] The narcotic antagonists include, for example, levallorphan tartrate, naloxone hydrochloride and nalorphine hydrochloride.

[0032] The antitubercular agents include, for example, isoniazid, ethambutol and sodium para-aminosalicylate.

[0033] The hormones include, for example, dexamethasone sodium sulfate, prednisolone sodium phosphate, prednisolone sodium hemisuccinate, methimazole, betamethasone sodium phosphate, hexestrol phosphate and hexestrol acetate.

[0034] The preparations of the present invention may contain a polylactic acid homopolymer or copolymer matrix and the above-mentioned physiologically active substances in admixture with other pharmaceutically acceptable substances usually used for preparing pharmaceutical preparations such as a solid diluent, a carrier, a binder, an adjuvant and an excipient. Suitable examples of such pharmaceutically acceptable substances are tragacanth, gum arabic, corn starch, gelatin, alginic acid, magnesium stearate, albumin, aluminum monostearate, yellow beeswax, sucrose, lactose, methylparaben, propylparaben, mannitol, propylene glycol, microcrystalline cellulose, calcium silicate, silica, polyvinylpyrrolidone, cacao butter, polyoxyethylene sorbitan monolaurate, ethyl lactate, sorbitan trioleate, ethyl laurate, calcium stearate, talc, oleic acid and linoleic acid.

[0035] The above physiologically active substance may be contained in the pharmaceutical preparations of the present invention in an amount ranging from about 0.01 to about 60 % (W/W, hereinafter the same), more preferably from about 0.1 to about 50 %, based on an amount of the polylactic acid high molecular weight compound although it may vary depending on the kinds of the employed drug, the desired pharmacological effects, sustained releasing time, and the like.

[0036] A size of the microsphere of the present invention is preferably in a range of from several nanometers to several hundred nanometers and can be controlled in accordance with objects, such as easiness for intravenous injection, directing to lymphocyte, easiness for intramuscular injection, or accumulation in a tissue of reticuloendothelial system (RES) such as liver, lung or pancrea. A distribution of the size is preferably as narrow as possible, but an appropriate distribution may be done by sieving.

[0037] The polylactic acid of the present invention is selected from the group of poly-L-lactic acid, poly-D,L-lactic acid, a copolymer of L-lactic acid - glycolic acid and a copolymer of D,L-lactic acid and glycolic acid, and the most suitable polylactic acid can be selected in accordance with a hydrolysis rate, a compatibility with used drug, or the like, suitable for the objects. The polylactic acid of the present invention may preferably have a weight average molecular weight ranging from 3,000 to 500,000, more preferably from 3,000 to 20,000 (in a range of an oligomer molecule), though the

present invention is not limited thereto.

[0038] The hydrophilic organic solvent used in the present invention is preferably an organic solvent which is well miscible with water at any ratio but immiscible with a poor solvent of the polylactic acid, including acetonitrile, dioxane, acetone, ethyl alcohol, methyl alcohol, tetrahydrofuran, dimethylformamide, dimethylacetamide, phenol, dimethyl sulfoxide, propyl alcohol, glycerol and ethylene glycol. Among these, acetonitrile and dioxane are particularly preferable.

[0039] The organic acid for dissolving the polylactic acid is preferably acetic acid, formic acid, glycolic acid or lactic acid, most preferably acetic acid. A derivative of acetic acid may also be used, which includes methyl acetate, ethyl acetate, trichloroacetic acid, trifluoroacetic acid, or an acetic acid salt such as sodium acetate, calcium acetate or potassium acetate. When acetic acid is used as the organic acid, it is preferred to use glacial acetic acid. However, in case of a drug hardly soluble in glacial acetic acid such as a protein having a high molecular weight, 80 to 90 % acetic acid is preferably employed. On the other hand, when acetonitrile or dioxane is employed as the organic solvent, a mixture of the organic solvent and water is preferably employed in a ratio of 70 : 30 to 99.9 : 0.1 (by weight, hereinafter the same), more preferably in a ratio of 80 : 20 to 95 : 5 since 100 % acetonitrile or dioxane poorly dissolves the polypeptide type active substance.

[0040] The poor solvent of the present invention is preferably a solvent which is substantially noncompatible with the solvent for dissolving the physiologically active substance and the polylactic acid and can be readily removed from the preparations after formulating, and includes silicone oil, liquid paraffin, vegetable oils such as cotton oil, sesame oil, castor oil and cone oil, or animal oils such as whale oil, and organic solvents such as toluene, xylene and hexane.

[0041] The polylactic acid type microsphere containing the water soluble physiologically active substance according to the present invention can be prepared by the solvent evaporation drying method, that is, by drying in an O/O type emulsion (i.e. oil in oil emulsion) in case that the mixture of organic solvent/water is used as the solvent, or by drying in a W/O type emulsion (i.e. water in oil emulsion) in case that acetic acid is used as the solvent. For facilitating the formulation, an emulsifying agent is preferably employed. The emulsifying agent includes any conventional emulsifying agents insofar as they can form a stable O/O or W/O type emulsion and are preferably nonionic surfactants such as those having HLB of 3 to 6.5, for example, sorbitan monostearate, sorbitan distearate, sorbitan monooleate, sorbitan sesquileate, sorbitan trioleate and lecithin. These hydrophobic emulsifying agents are usually added in an amount ranging from 0.1 to 5 parts by weight (hereinafter the same), preferably from 1 to 3 parts, based on 100 parts of the hydrophobic medium. Emulsification can be carried out by any known dispersion procedures, such as a propeller stirring method, a colloid mill method, a homogenizer method, an ultrasonic radiation method or a microfluidizer method. The ultrasonic radiation method is preferably employed in order to obtain microspheres having a size of several micron. On the other hand, the microfluidizer method is preferably employed in order to obtain microspheres having a size of several tens of nanometer to several hundreds of nanometer.

[0042] From the O/O type or W/O type emulsion thus prepared by emulsification procedure such as the ultrasonic radiation method, the solvent for dissolving both polymer and physiologically active substance is distilled off to produce the polylactic acid type microsphere containing the physiologically active substance. The thus obtained microspheres are separated from the poor solvent by means of filtration or centrifugation, washed with an organic solvent such as acetone or hexane to remove the poor solvent remained on the surface of the microspheres, and then dried.

[0043] The polylactic acid type microspheres containing a water soluble physiologically active substance according to the present invention can be used in the form of injections, preparations for oral administration, preparations for percutaneous administration, suppositories, preparations for pernasal administration, preparations for administration in oral cavity and intraocular preparations.

[0044] The polylactic acid type microspheres containing a water soluble physiologically active substance of the present invention is advantageous in that the water soluble physiologically active substance can be uniformly incorporated into the polylactic acid type high molecular weight compound without loss of the activity, whereby occurrence of undesirable burst is inhibited and the active substance is gradually released for a long time of period of more than one week and the incorporation rate of the active substance into the microsphere is increased to more than 90 %.

Example 1

[0045] A solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (1 g) dissolved in acetonitrile (9 ml) was mixed with a solution of adriamycin powder (50 mg) dissolved in distilled water (1 ml) and the mixture was stirred with magnetic stirrer. The obtained solution was added dropwise to cotton oil (100 ml) containing Span 80 (2 wt %) as surfactant while stirring with a propeller type stirrer. After the mixture was heated at 40 to 60°C to distil off the mixed solvent of acetonitrile and water, the obtained residue was centrifuged and washed with n-hexane to prepare polylactic acid type microspheres containing adriamycin having a mean particle size of 20 to 30 μm . Table 1 shows results of *in vitro* elution experiment wherein a fixed amount of the microspheres in phosphate buffer (pH 7.4) was placed in an incubator with shaker at 37° C and the concentration of the active substance was measured by a fluorescent method.

Comparative Example 1

[0046] To a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (1 g) dissolved in methylene chloride (10 ml) was added adriamycin powder (50 mg) and the mixture was stirred with magnetic stirrer. Thereafter, the procedure of Example 1 was repeated to prepare polylactic acid type microspheres containing adriamycin. Table 1 shows results of the in vitro elution experiment.

Example 2

[0047] The procedure of Example 1 was repeated except that poly-L-lactic acid having a weight average molecular weight of about 7,500 to prepare poly-L-lactic acid type microspheres containing adriamycin. Table 1 shows results of the in vitro elution experiment.

Example 3

[0048] The procedure of Example 1 was repeated except that L-lactic acid-glycolic acid copolymer (copolymerization ratio 7:3) having a weight average molecular weight of about 7,000 to prepare poly-L-lactic acid type microspheres containing adriamycin. Table 1 shows results of the in vitro elution experiment.

Example 4

[0049] A solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (1 g) dissolved in acetonitrile (9 ml) was mixed with a solution of tobramycin powder (200 mg) dissolved in distilled water (1 ml) and the mixture was stirred with magnetic stirrer. Thereafter the procedure of Example 1 was repeated to prepare polylactic acid type microspheres containing tobramycin. Table 2 shows results of the in vitro elution experiment, which was carried out in the same manner as in Example 1 except that the concentration of the active substance was measured by bioassay procedure using Bacillus subtilis.

Comparative Example 2

[0050] To a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (1 g) dissolved in methylene chloride (10 ml) was added tobramycin powder (200 mg) and the mixture was stirred with magnetic stirrer. Thereafter, the procedure of Example 1 was repeated to prepare polylactic acid type microspheres containing tobramycin. Table 2 shows results of the in vitro elution experiment.

Example 5

[0051] A solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (1 g) dissolved in acetonitrile (8 ml) was mixed with a solution of cisplatin (2 mg) dissolved in distilled water (2 ml) and the mixture was stirred with magnetic stirrer. Thereafter, the procedure of Example 1 was repeated to prepare polylactic acid type microspheres containing cisplatin. The incorporation rate of the active substance into microspheres was almost 100 %. The in vitro elution experiment was carried out in the same manner as in Example 2 except that the measurement of the elution amount was carried out by atomic absorption spectrometry.

Comparative Example 3

[0052] A solution of cisplatin (2 mg) dissolved in 20 % aqueous solution of gelatin (2 mg) was added to 20 % solution (10 ml) of poly-L-lactic acid having a weight average molecular weight of about 3,600 in methylene chloride and the mixture was emulsified with ultrasonic to prepare a W/O type emulsion, which was cooled quickly to gelate the gelatin layer. The resultant was poured into 1 % aqueous solution of polyvinyl alcohol (100 mg) which has previously been ice-cooled, and the mixture was dispersed with a homogenizer to prepare a W/O/W type emulsion. Then, methylene chloride was evaporated and the residue was dried to prepare polylactic acid type microcapsules of gelatin containing cisplatin. The incorporation rate of cisplatin into the microcapsules was only about 29 %. Table 2 shows results of the in vitro elution experiment.

Example 6

[0053] A solution of L-lactic acid-glycolic acid copolymer (copolymerization ratio; 80 : 20) having a weight average

molecular weight of 12,000 (2 g) dissolved in glacial acetic acid (20 ml) and a solution of luteinizing hormone releasing hormone (LHRH; N-Ac[D-P-CI-Phe^{1,2}, D-Trp³, D-Arg⁶, D-Ala¹⁰]-LH-RH) (200 mg) dissolved in distilled water (2 ml) were mixed with each other while stirring with magnetic stirrer. The mixture did not become cloudy and remained still clear, showing a complete dissolution of both the polymer and the active substance. This solution was added dropwise to sesame oil (200 ml) containing 1 wt % of lecithin as a surfactant while stirring with a propeller type stirrer and further emulsified with a ultrasonic homogenizer. After acetic acid and water were evaporated with heating at 40° to 60° C, the residue was centrifuged, washed with n-hexane and dried to prepare polylactic acid type microspheres containing LHRH with an average particle size of from 0.5 to 5 µm.

[0054] The obtained microspheres were dispersed in refined sesame oil and subcutaneously injected into female rats weighing about 350 g in an amount of 12 mg/kg of LHRH. The effect of LHRH on living body, i.e. atrophy of genital system organ due to desensitization of hypophysis-gonad system, was observed for a long period of time. As a result, the effect continued for about 80 days.

Example 7

[0055] A solution of poly-L-lactic acid having a weight average molecular weight of 16,000 (2 g) dissolved in glacial acetic acid (20 mg) and a solution of pig insulin (powder manufactured by Sigma, 100 mg) dissolved in 0.1 N HCl (2 ml) were mixed with each other while stirring with magnetic stirrer. The mixture did not become cloudy and remained clear. Thereafter, the procedure of Example 6 was repeated to prepare polylactic acid type microspheres containing insulin. Table 3 shows results of the *in vitro* elution experiment wherein the insulin concentration was measured by glucose oxidase method (enzyme method).

Comparative Example 4

[0056] To a solution of poly-D,L-lactic acid having a weight average molecular weight of 16,000 (2 g) dissolved in chloroform (20 ml) was added insulin powder (100 mg) and the mixture was stirred with magnetic stirrer. Thereafter, the procedure of Example 7 was repeated to prepare a polylactic acid type microspheres containing insulin. Table 3 shows results of the *in vitro* elution experiment.

Example 8

[0057] A lactic acid-glycolic acid copolymer (copolymerization ratio; 80 : 20) having a weight average molecular weight of 7,600 (2 g) and calcitonin (10,000 U) were dissolved in 98 % acetic acid (20 ml) while stirring with magnetic stirrer. Thereafter, the procedure of Example 6 was repeated to prepare polylactic acid type microspheres containing calcitonin. Measurement of serum calcium lowering activity proved no decrease of the calcitonin activity. The incorporation rate of calcitonin into polylactic acid type microspheres was about 95 %. Table 3 shows results of the *in vitro* elution experiment wherein the measurement of the elution amount was carried out by HPLC as in Example 1.

Comparative Example 5

[0058] The procedure of Comparative Example 3 was repeated except that calcitonin (10,000 U) was used to prepare a W/O/W emulsion and further to prepare a polylactic acid type microcapsules of gelatin containing calcitonin. The incorporation rate of calcitonin into the polylactic acid type microcapsules was about 53 %. Table 3 shows results of the *in vitro* elution experiment.

Example 9

[0059] A solution of lactic acid-glycolic acid copolymer (copolymerization ratio; 75 : 25) having a weight average molecular weight of about 5,300 (1 g) and each 1 X 10⁸ U of mouse interferon α and interferon γ dissolved in 92 % acetic acid (10 ml) was added dropwise to sesame oil (100 ml) containing 1 wt% lecithin as surfactant. The mixture was emulsified with microfluidizer (M-110H, manufactured by Microfluidics Corporation) and subjected to drying-in-liquid method to prepare polylactic acid type microspheres containing interferon with an average particle size of from 100 to 500 nm. The incorporation rate of interferon into microspheres was about 98 %.

Example 10

[0060] Meth-A fibrosarcoma cells derived from BALB/C mice were intraperitoneally implanted into BALB/C in an amount of 2 X 10⁶ cells per animal. Three days after implantation, the polylactic acid type microspheres containing

mouse interferon α prepared in Example 9 was intraperitoneally administered into the animal on every third day. Ten days after implantation, the number of Meth-A cells in the abdomen and life-prolonging effect of the mouse were evaluated. The obtained results are shown in Table 4.

5 Comparative Example 6

[0061] The procedure of Comparative Example 3 was repeated except that mouse interferon α (1×10^8 U) was used to prepare a W/O/W emulsion and further to prepare a polylactic acid type microcapsules of gelatin containing interferon α . The incorporation rate of interferon into the microcapsule was about 47 %. The *in vivo* experiment was carried out as in Example 10. The results are shown in Table 4.

Example 11

[0062] The procedure of Example 9 was repeated except that a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (500 mg) and human tumor necrosis factor (TNF) (7.8×10^5 U) dissolved in 88 % acetic acid (10 ml) were used to prepare polylactic acid type microspheres containing TNF. The *in vitro* elution experiment of Example 1 was repeated where the measurement of elution amount was carried out by enzyme immunoassay. As a result, the activity continued for 30 days.

20 Example 12

[0063] The procedure of Example 9 was repeated except that a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (500 mg) and human interleukin II (1×10^6 U) dissolved in 88 % acetic acid (10 ml) were used to prepare polylactic acid type microspheres containing interleukin II.

25 [0064] The obtained microspheres were injected into mouse blood and the blood level of IL-II was measured by using IL-II dependent cell line, CTLL-2. The result showed a high concentration of IL-II of not less than 1×10^3 U/ml for 96 hours.

Example 13

30 [0065] The procedure of Example 6 was repeated except that a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (500 mg) and rat epidermal growth factor (EGF) (0.5 mg) dissolved in 90 % acetic acid (20 ml) were used to prepare polylactic acid type microspheres containing EGF.

35 [0066] The obtained microspheres were subcutaneously administered to carotid-intubated rat and the serum level of EGF was measured by radioimmunoassay. The result showed an increase of the serum level of EGF which was found on the second day and continued for about 30 days.

Example 14

40 [0067] The procedure of Example 8 was repeated except that a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (500 mg) and urokinase (6×10^5 U) dissolved in glacial acetic acid were used to prepare polylactic acid type microspheres containing urokinase. The *in vitro* elution experiment was carried out and the enzyme activity was measured by fibrin plate method. The result showed urokinase of not less than 1,000 U for about 4 weeks.

45 Example 15

[0068] The procedure of Example 6 was repeated except that a solution of poly-L-lactic acid having a weight average molecular weight of about 3,600 (500 mg) and prolactin (100 mg) dissolved in glacial acetic acid were used to prepare polylactic acid type microspheres containing prolactin. The obtained microspheres were subcutaneously administered to rat and the serum level of prolactin was measured by radioimmunoassay. The result showed a high concentration of prolactin for about 60 days.

Example 16

55 [0069] The procedure of Example 1 was repeated except that a solution of poly-L-lactic acid having a weight average molecular weight of about 4,700 (1 g) and panimycin (dibekacin sulfate) (100 mg) dissolved in a mixture of acetonitrile and water (9:1) (20 ml) were used to prepare polylactic acid type microspheres containing panimycin. The obtained

EP 0 330 180 B2

microspheres were subjected to the *in vitro* elution experiment wherein the duration of the antimicrobial activity was measured by bioassay using *Bacillus subtilis*. The result proved that a high concentration of not less than 10 µg/ml of panimycin was continued for about 30 days.

Table 1

Elution (day)	Cumulative elution of adriamycin (%)			
	Ex. 1	Ex. 2	Ex. 3	Comp. Ex. 1
1	24.5	9.3	12.2	33.6
3	28.1	11.7	24.3	91.3
4	37.3	20.2	31.6	100.0
14	56.6	29.3	42.6	-
21	78.2	41.5	55.1	-
28	89.4	53.8	67.3	-
42	100.0	69.1	81.7	-
56	-	84.6	100.0	-
68	-	100.0	-	-

Table 2

Elution (day)	Cumulative elution of tobramycin (%)		Cumulative elution of cisplatin (%)	
	Ex. 4	Comp. Ex. 2	Ex. 5	Comp. Ex. 3
1	29.5	93.5	21.7	35.4
3	42.1	100.0	35.4	86.5
7	65.7	-	53.2	100.0
14	63.5	-	71.7	-
28	91.4	-	95.3	-
42	100.0	-	100.0	-

Table 3

Elution (day)	Cumulative elution of insulin (%)		Cumulative elution of calcitonin (%)	
	Ex. 7	Comp. Ex. 4	Ex. 8	Comp. Ex. 5
1	21.2	71.3	13.6	51.3
4	48.3	100.0	23.5	92.4
8	63.5	-	49.7	100.0
12	74.7	-	66.9	-
16	87.9	-	91.2	-
20	96.3	-	98.5	-

Table 4

	Meth-A cell No. ($\times 10^5$)	Survival date (day)
Ex. 10	405 \pm 263	60
Ex. 6	952 \pm 287	14

Claims

1. A microsphere, which comprises polylactic acid selected from the group consisting of an L-lactic acid polymer, a D,L-lactic acid polymer, a copolymer of L-lactic acid and glycolic acid and a copolymer of D,L-lactic acid and glycolic acid, and a water soluble physiologically active substance, selected from the group consisting of a polypeptide type or proteinaceous substance, an antimicrobial agent, an antitumor agent, an antipyretic, an antiinflammatory agent, an analgesic, an antitussive, an expectorant, an antidepressant, a muscle relaxant, an antiulcer agent, an antiallergic agent, a hypotensive, a diuretic, an antidiabetic, a cardiotonic, a vasodilating agent, an antiarrhythmic agent, an anticoagulating agent, a hemostatic agent, a narcotic antagonist, an antitubercular agent, a hormone, an immunoactivator, an antiepileptic agent, an antihistaminic and an agricultural agent, wherein the water-soluble physiologically active substance is uniformly incorporated into the polylactic acid,
and has a mean particle size of from about 0.01 μm to 300 μm having not more than 30% of an eluted amount of said physiologically active substance based on the content of said physiologically active substance in the microsphere after 24 hours in in vitro elution test in phosphate buffer of pH 7.4 at 37°C obtainable by a process, which comprises preparing a solution of the water soluble physiologically active substance and the polylactic acid uniformly dissolved in a mixed solvent comprising a hydrophilic organic solvent and water or in an organic acid, mixing the solution with a poor solvent immiscible with said mixed solvent or organic acid to give an O/O type or W/O type emulsion, and subjecting the emulsion to solvent evaporation drying.
2. A process for preparing a microsphere which comprises polylactic acid selected from the group consisting of an L-lactic acid polymer, a D,L-lactic acid polymer, a copolymer of L-lactic acid and glycolic acid and a copolymer of D,L-lactic acid and glycolic acid, and a water soluble physiologically active substance, selected from the group consisting of a polypeptide type or proteinaceous substance, an antimicrobial agent, an antitumor agent, an antipyretic, an antiinflammatory agent, an analgesic, an antitussive, an expectorant, an antidepressant, a muscle relaxant, an antiulcer agent, an antiallergic agent, a hypotensive, a diuretic, an antidiabetic, a cardiotonic, a vasodilating agent, an antiarrhythmic agent, an anticoagulating agent, a hemostatic agent, a narcotic antagonist, an antitubercular agent, a hormone, an immunoactivator, an antiepileptic agent, an antihistaminic and an agricultural agent, wherein the water-soluble physiologically active substance is uniformly incorporated into the polylactic acid,
and has a mean particle size of from about 0.01 μm to 300 μm having not more than 30% of an eluted amount of said physiologically active substance based on the content of said physiologically active substance in the microsphere after 24 hours in in vitro elution test in phosphate buffer of pH 7.4 at 37°C
, which comprises preparing a solution of the water soluble physiologically active substance and the polylactic acid uniformly dissolved in a mixed solvent comprising a hydrophilic organic solvent and water or in an organic acid, mixing the solution with a poor solvent immiscible with said mixed solvent or organic acid to give an O/O type or W/O type emulsion, and subjecting the emulsion to solvent evaporation drying.
3. The process of claim 2 wherein said hydrophilic organic solvent for the solvent of the polylactic acid is a member selected from the group consisting of acetonitrile, dioxane, acetone, ethyl alcohol, methyl alcohol, tetrahydrofuran, dimethylformamide, dimethylacetamide, phenol, dimethyl sulfoxide, propyl alcohol, glycerol and ethylene glycol.
4. The process of claim 2 wherein said organic acid for the solvent of the polylactic acid is a member selected from the group consisting of acetic acid and formic acid.
5. The process of claim 2 wherein said poor solvent immiscible with the mixed solvent or the organic acid is a member selected from the group consisting of silicone oil, liquid paraffin, cotton oil, sesame oil.

Patentansprüche

1. Mikrokugel, enthaltend Polymilchsäure, ausgewählt aus der Gruppe, bestehend aus einem L-Milchsäurepolymeren, einem D,L-Milchsäurepolymeren, einem Copolymeren aus L-Milchsäure und Glykolsäure und einem Copolymeren aus D,L-Milchsäure und Glykolsäure, und eine wasserlösliche, physiologisch aktive Substanz, ausgewählt aus der Gruppe, bestehend aus einer Substanz vom Polypeptidtyp oder einer proteinartigen Substanz, einem antimikrobiellen Mittel, einem Antitumormittel, einem Antipyretikum, einem antiinflammatorischen Mittel, einem Analgetikum, einem Antitussivum, einem Expektorans, einem Antidepressivum, einem Muskelrelaxans, einem Antiulcermittel, einem Antiallergikum, einem Hypotensivum, einem Diuretikum, einem Antidiabetikum, einem Kardiotonikum, einem Vasodilatator, einem Antiarrhythmikum, einem Antikoagulans, einem Hämostatikum, einem Narkoseantagonisten, einem Antituberkulosemittel, einem Hormon, einem Immunaktivator, einem Antiepileptikum, einem Antihistaminikum und einem landwirtschaftlichen Mittel, umfaßt, wobei die wasserlösliche physiologisch aktive Substanz einheitlich in die Polymilchsäure eingearbeitet ist und eine mittlere Teilchengröße von etwa 0,01 µm bis 300 µm besitzt, wobei die eluierte Menge der physiologisch aktiven Substanz, bezogen auf den Gehalt der physiologisch aktiven Substanz in der Mikrokugel, nach 24 h bei dem in vitro Elutionstest in Phosphatpuffer mit einem pH-Wert von 7,4 bei 37°C nicht mehr als 30 % beträgt, erhalten gemäß einem Verfahren, umfassend die Herstellung einer Lösung der in Wasser löslichen, physiologisch aktiven Substanz und der Polymilchsäure, die gleichförmig in einem Mischlösungsmittel aus einem hydrophilen organischen Lösungsmittel und Wasser oder in einer organischen Säure aufgelöst sind, Vermischen der Lösung mit einem schlechten Lösungsmittel, das mit dem Mischlösungsmittel oder der organischen Säure nicht-mischbar ist, um eine Emulsion vom O/O-Typ oder W/O-Typ herzustellen und Trocknen der Emulsion durch Lösungsmittelverdampfung.
2. Verfahren zur Herstellung einer Mikrokugel, enthaltend Polymilchsäure, ausgewählt aus der Gruppe, bestehend aus einem L-Milchsäurepolymeren, einem D,L-Milchsäurepolymeren, einem Copolymeren aus L-Milchsäure und Glykolsäure und einem Copolymeren aus D,L-Milchsäure und Glykolsäure, und eine wasserlösliche, physiologisch aktive Substanz, ausgewählt aus der Gruppe, bestehend aus einer Substanz vom Polypeptidtyp oder einer proteinartigen Substanz, einem antimikrobiellen Mittel, einem Antitumormittel, einem Antipyretikum, einem antiinflammatorischen Mittel, einem Analgetikum, einem Antitussivum, einem Expektorans, einem Antidepressivum, einem Muskelrelaxans, einem Antiulcermittel, einem Antiallergikum, einem Hypotensivum, einem Diuretikum, einem Antidiabetikum, einem Kardiotonikum, einem Vasodilatator, einem Antiarrhythmikum, einem Antikoagulans, einem Hämostatikum, einem Narkoseantagonisten, einem Antituberkulosemittel, einem Hormon, einem Immunaktivator, einem Antiepileptikum, einem Antihistaminikum und einem landwirtschaftlichen Mittel, umfaßt, wobei die wasserlösliche physiologisch aktive Substanz einheitlich in die Polymilchsäure eingearbeitet ist und eine mittlere Teilchengröße von etwa 0,01 µm bis 300 µm besitzt, wobei die eluierte Menge der physiologisch aktiven Substanz, bezogen auf den Gehalt der physiologisch aktiven Substanz in der Mikrokugel, nach 24 h bei dem in vitro Elutionstest in Phosphatpuffer mit einem pH-Wert von 7,4 bei 37°C nicht mehr als 30 % beträgt, umfassend die Herstellung einer Lösung der in Wasser löslichen, physiologisch aktiven Substanz und der Polymilchsäure, die gleichförmig in einem Mischlösungsmittel aus einem hydrophilen organischen Lösungsmittel und Wasser oder in einer organischen Säure aufgelöst sind, Vermischen der Lösung mit einem schlechten Lösungsmittel, das mit dem Mischlösungsmittel oder der organischen Säure nicht-mischbar ist, um eine Emulsion vom O/O-Typ oder W/O-Typ herzustellen und Trocknen der Emulsion durch Lösungsmittelverdampfung.
3. Verfahren nach Anspruch 2, dadurch gekennzeichnet, daß das hydrophile, organische Lösungsmittel für das Lösungsmittel der Polymilchsäure eine Verbindung, ausgewählt aus der Gruppe, bestehend aus Acetonitril, Dioxan, Aceton, Ethylalkohol, Methylalkohol, Tetrahydrofuran, Dimethylformamid, Dimethylacetamid, Phenol, Dimethylsulfoxid, Propylalkohol, Glycerin und Ethylenglykol ist.
4. Verfahren nach Anspruch 2, dadurch gekennzeichnet, daß die organische Säure für das Lösungsmittel der Polymilchsäure eine Verbindung, ausgewählt aus der Gruppe, bestehend aus Essigsäure und Ameisensäure, ist.
5. Verfahren nach Anspruch 2, dadurch gekennzeichnet, daß das schlechte Lösungsmittel, das mit dem Mischlösungsmittel oder der organischen Säure nicht-mischbar ist, eine Verbindung, ausgewählt aus der Gruppe, bestehend aus Siliconöl, flüssigem Paraffin, Baumwollöl, Sesamöl, Rizinusöl, Zapfenöl, Walöl, Toluol, Xylol und Hexan, ist.

Revendications

1. Microsphère qui comprend un acide polylactique choisi dans le groupe constitué par un polymère d'acide L-lacti-

que, un polymère d'acide D,L-lactique, un copolymère d'acide L-lactique et d'acide glycolique et un copolymère d'acide D,L-lactique et d'acide glycolique, et une substance physiologiquement active soluble dans l'eau choisie dans le groupe constitué par des substances de type polypeptidique ou protéiniques, des agents antimicrobiens, des agents antitumoraux, des antipyrétiques, des agents antiinflammatoires, des analgésiques, des antitussifs, des expectorants, des antidépresseurs, des myorelaxants, des agents antiulcères, des agents antiallergiques, des hypotenseurs, des diurétiques, des antidiabétiques, des cardiotoniques, des agents vasodilatateurs, des agents antiarythmiques, des agents anticoagulants, des agents hémostatiques, des antagonistes de narcotiques, des agents antituberculeux, des hormones, des immunoactivateurs, des agents antiépileptiques, des anti-histaminiques et des agents phytosanitaires, où la substance physiologiquement active soluble dans l'eau est incorporée uniformément dans l'acide polylactique, et a une taille de particules moyenne comprise entre environ 0,01 μm et 300 μm , et qui, dans un essai d'élution *in vitro* dans un tampon de phosphate de pH 7,4 à 37°C, présente au bout de 24 heures une quantité éluee de ladite substance physiologiquement active d'au plus 30 % du contenu de ladite substance physiologiquement active dans la microsphère, que l'on peut obtenir par un procédé qui comprend la préparation d'une solution de la substance physiologiquement active soluble dans l'eau et de l'acide polylactique dissous uniformément dans un solvant mixte comprenant un solvant organique hydrophile et de l'eau ou dans un acide organique, le mélange de la solution avec un piètre solvant immiscible audit solvant mixte ou audit acide organique pour donner une émulsion de type huile/huile ou eau/huile, et la soumission de l'émulsion à un séchage par évaporation du solvant..

2. Procédé de préparation de microsphères comprenant un acide polylactique choisi dans le groupe constitué par un polymère d'acide L-lactique, un polymère d'acide D,L-lactique, un copolymère d'acide L-lactique et d'acide glycolique et un copolymère d'acide D,L-lactique et d'acide glycolique, et une substance physiologiquement active soluble dans l'eau choisie dans le groupe constitué par des substances de type polypeptidique ou protéiniques, des agents antimicrobiens, des agents antitumoraux, des antipyrétiques, des agents antiinflammatoires, des analgésiques, des antitussifs, des expectorants, des antidépresseurs, des myorelaxants, des agents antiulcères, des agents antiallergiques, des hypotenseurs, des diurétiques, des antidiabétiques, des cardiotoniques, des agents vasodilatateurs, des agents antiarythmiques, des agents anticoagulants, des agents hémostatiques, des antagonistes de narcotiques, des agents antituberculeux, des hormones, des immunoactivateurs, des agents antiépileptiques, des anti-histaminiques et des agents phytosanitaires, où la substance physiologiquement active soluble dans l'eau est incorporée uniformément dans l'acide polylactique, et a une taille de particules moyenne comprise entre environ 0,01 μm et 300 μm , et qui, dans un essai d'élution *in vitro* dans un tampon de phosphate de pH 7,4 à 37°C, présente au bout de 24 heures une quantité éluee de ladite substance physiologiquement active d'au plus 30 % du contenu de ladite substance physiologiquement active dans la microsphère, qui comprend la préparation d'une solution de la substance physiologiquement active soluble dans l'eau et de l'acide polylactique dissous uniformément dans un solvant mixte comprenant un solvant organique hydrophile et de l'eau ou dans un acide organique, le mélange de la solution avec un piètre solvant immiscible audit solvant mixte ou audit acide organique pour donner une émulsion de type huile/huile ou eau/huile, et la soumission de l'émulsion à un séchage par évaporation du solvant.

3. Procédé selon la revendication 2 dans lequel ledit solvant organique hydrophile servant de solvant de l'acide polylactique est un membre choisi dans le groupe constitué par l'acétonitrile, le dioxane, l'acétone, l'alcool éthylique, l'alcool méthylique, le tétrahydrofurane, le diméthylformamide, le diméthylacétamide, le phénol, le diméthylsulfoxyde, l'alcool propylique, le glycérol et l'éthylèneglycol.

4. Procédé selon la revendication 2 dans lequel ledit acide organique servant de solvant de l'acide polylactique est un membre choisi dans le groupe constitué par l'acide acétique et l'acide formique.

5. Procédé selon la revendication 2 dans lequel ledit piètre solvant non miscible au solvant mixte ou à l'acide organique est un membre choisi dans le groupe constitué par une huile de silicone, une paraffine liquide, l'huile de coton, l'huile de sésame.